

5025 Silver Conductor

Polymer Thick Film Composition

All values reported here are results of experiments in our laboratories intended to illustrate product performance potential with a given experimental design. They are not intended to represent the product's specifications.

Product Description

Silver conductor 5025 is used to fabricate low voltage circuitry, especially on flexible substrates. It should be used as an alternative to 5007 when faster drying conditions are required, or when design considerations dictate a higher operating use temperature. It can be used with manual, semi-automatic, and reel-to-reel equipment.

Product Benefits

- Best general purpose Ag for higher temperature operations

Processing

- **Screen Printing Equipment**
Reel-to-reel, Semiautomatic, manual
- **Substrates**
Polyester, polyimide, paper, epoxy glass
- **Ink Residence Time on Screen**
> 2 hours
- **Screen Types**
Stainless steel, Polyester
- **Typical Cure Conditions**
Box Oven: 120°C for 5 - 6 minutes
Reel-to-reel: 140°C for 1 minute
- **Typical Circuit Line Thickness Printed with 325-mesh stainless steel screen**
12 - 15 microns
- **Clean-up Solvent**
Ethylene diacetate or methyl propasol acetate

Storage and Shelf Life

DuPont thick film polymeric compositions should be stored at ambient temperatures. The shelf life of material in unopened containers is a minimum of six months from date of shipment. Some settling of solids may occur, so compositions should be stirred thoroughly prior to use.

Table 1
Typical Physical Properties on 5-mil Polyester Film

Sheet Resistivity (mΩ/sq/mil)*	12 - 15
Resistivity after Flex (mΩ/sq/mil) 15 sec after test Crease (180°, 1 cycle)	≤ 50
Adhesion/Tape Pull (3M Scotch Tape #810)	No Ag Transfer
Abrasion Resistance, Pencil Hardness (ASTM D3363-74)	≥ 1H
Operating Use Temperature (°C)	≤ 90
Solderability	Not Recommended
Change in Physical Properties after Environment Tests [†]	Insignificant
Change in Electrical Properties after Environmental Tests [†]	<10%

* Environmental Tests
 • Thermal Shock (+85°C to -40°C, 30 min. each, 5 cycles)
 • Dry Heat (+85°C, 20 days)
 • Humidity (+60°C, 95% RH, 10 days) [MIL Std 202E, method 103, cond. A]
 • Salt Spray (+35°C, 5% salt, 10 days) [ASTM B117]
 • Silver Migration (1 V DC/mil gap, +40°, 90% RH, 500 hr, tested on 40 and 70-mil gaps)
 • Sulfate Dioxide (+45°C, 90% RH, 500 hrs in a 9-liter chamber containing 500 mg of flowers of sulfur)

Dry

Dry and cure in a well ventilated oven or conveyor dryer where the exhaust meets environmental regulations. See Safety & Handling section for additional information.

Table 2 Composition Properties	
Viscosity (Pa.s) (Brookfield 0.5RVT, 5 rpm, #14 spindle, 25°C)	20 - 30
Solids (150°C) (%)	68 - 72
Coverage (cm ² /g) (Dependent on screen size and material)	230 - 120
Thinner	8210

Safety and Handling

DuPont thick film products are intended for industrial use by trained personnel. These products contain organic and inorganic ingredients. It is important for workers to avoid overexposure to chemicals contained in these products or that might become available when processing them. Overexposure to other materials used in the operation should also be avoided, for example, cleaning solvents and degreasing fluids.

Well-designed area and personal air sampling/analysis can show if exposures are within required and recommended limits. Properly designed engineering controls, such as local ventilation and process enclosures, are effective in limiting employee exposure and to avoid the creation of hazardous conditions (e.g. forming an explosive vapor concentration). Engineering controls and procedures must comply with all applicable federal, state and local safety, health and environmental laws and regulations.

The following additional precautions should be taken when handling these products:

- Read the Material Safety Data Sheet (MSDS) and product labels before using the products;
- Use appropriate personal protective equipment (PPE) and practice good industrial hygiene. **DO NOT INGEST! DANGEROUS IF SWALLOWED!**
- Keep product container closed when not in use to prevent solvent evaporation and spilling hazards;
- If contact with skin occurs, wash affected area immediately with soap and water
- Avoid prolonged breathing of vapors and dusts/particulates. Keep exposure levels within the required or recommended limits. Always use sufficient ventilation as noted above

United States

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

DuPont (UK) Limited
Coldharbour Lane
Frenchay
Bristol BS16 1QD
England
Tel.: 44-117-931-3191

Japan

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome,
Chiyoda-ku, Tokyo 100-6111
Japan
Tel.: 81-35-521-8650

Visit our website at: <http://www.dupont.com/mcm>

The information given herein is based on data believed to be reliable, but DuPont makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

Caution: Do Not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102

Copyright © 2004 E.I. DuPont de Nemours and Company. All right reserved.

MCM5025 (09/2004) Printed in U.S.A.

