



93005LE 50 μ 300LSE Double Coated Tape

Technical Data

April 2015

Product Description

3M™ 93005LE is a 50 μ Double Coated Polyester Tape featuring 3M™ Type 300LSE Acrylic Adhesive. Performance features include good resistance to consumer chemicals and excellent anti-lifting properties. 3M type 300LSE acrylic adhesive has a long history of successfully bonding a wide variety of similar and dissimilar materials such as metals, most plastics, glass, papers, and painted surfaces.

Product Construction

3M™ 93005LE is a 50 μ Double Coated Polyester Tape featuring 300LSE adhesive and two Polycoated Kraft Release Liners.

Layer	Type	Thickness	
Release Liner 1	Polycoated Kraft	107 μ	4.2 mils
Adhesive - Faceside	300LSE Acrylic	19 μ	0.75 mils
Polyester Film	Transparent	12 μ	0.50 mils
Adhesive - Backside	300LSE Acrylic	19 μ	0.75 mils
Release Liner 2	Polycoated Kraft	157 μ	6.2 mils
Total Thickness: (including liners)		314 μ	12.4 mils
Total Thickness (without liners)		50 μ	1.97 mils

Notes: All tolerances +/- 10%

Typical Performance

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Property	Substrate	Dwell/Rate	Value	Units	Value	Units
Faceside Adhesive Peel Adhesion @ 180° ASTM D3330	Stainless Steel Stainless Steel	20 min @ RT	0.618	N/mm	56.5	oz/in
		72 hrs @ RT	0.790	N/mm	72.2	oz/in
Backside Adhesive Peel Adhesion @ 180° ASTM D3330	Stainless Steel Stainless Steel	20 min @ RT	0.770	N/mm	70.4	oz/in
		72 hrs @ RT	0.824	N/mm	75.3	oz/in
	ABS Polypropylene HDPE	72 hrs @ RT	0.619	N/mm	56.6	oz/in
		72 hrs @ RT	0.774	N/mm	70.7	oz/in
Dynamic Shear ASTM D1002	Stainless Steel	10mm/min	1.084	N/mm ²	157.2	psi
Tensile Strength ASTM D897	Stainless Steel	10mm/min	1.099	N/mm ²	159.4	psi
Impact Shear Strength ASTM D950	25x25mm Puck	Pendulum Impact	1.545	J		

Notes: Adhesion is by ASTM D3330 method with exceptions as noted
Stainless Steel substrate unless otherwise noted
Adhesive backer is 2 mil Polyester Film

3M™ 93005LE 50μ 300LSE Double Coated Tape

For Additional Information

To request additional product information or to arrange for sales assistance, call 3M Technical Service at 651-736-8205. Address correspondence to: 3M Industrial Adhesives and Tapes Division, 3M Center, Building 230-2E-10, St. Paul, MN 55144-1000.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Industrial Adhesives & Tapes Division Converter Markets

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
800-223-7427 651-778-4244 (fax)
www.3M.com/converter



Recycled Paper
40% pre-consumer
10% post-consumer

3M is a trademark of 3M Company.
Printed in U.S.A.
©3M 2015 (4/15)