





121110

PRODUCT DATA

10mil Clear Gloss/Gloss PVC Coated on 1 Side Tipped w/Backing Paper

Dura-Go™ substrates are Indigo-licensed and were jointly developed by Hanita Coatings, Tekra Corporation and Indigo to create the premier product line of film substrates for Indigo digital presses.

Our proprietary primer coatings provide a number of benefits, including:

Reliable, superior ink adhesion

High definition of colors

Long shelf life, guaranteed to print for one year after purchase when stored at less than 72F and less than 50% relative humidity.

The Dura-Go coating is highly resistant to weathering/degradation:

| | | Units | Test Conditions |
|---------------------|------|--------|------------------------------|
| Weatherability | 2 | Months | Outdoor |
| | 24 | Months | Indoor |
| Dish Washer | pass | N/A | 1.5 hours, top cycle |
| Water and | 200 | Hours | 100% RH at 100F |
| Chemical Resistance | 200 | Hours | Distilled Water at 90F |
| | 2 | Hours | Water + 2% detergent at 150F |
| | 24 | Hours | Ethanol at 75F |

Rigid vinyl is suitable for virtually all printing applications and offers a variety of print surfaces to fit your specific printing needs. Rigid vinyl print stock also offers excellent flex properties, embossed character retention and color consistency making it the ideal product for virtually all applications where long life, durability and performance are critical. Such applications include menus, POP displays and shelfdanglers.

Rigid vinyl physical properties include:

| Property | Test Method | Typical Values |
|-----------------------------------|-------------|---------------------------------------|
| Thickness Tolerance | | ± 5% |
| Gloss Value (60°) | ASTM-D523 | 135 ± 10 (lightly tinted transparent) |
| Specific Gravity | ASTM-D792 | 1.34 ± 0.02 |
| Tensile Strength (psi) | ASTM-D638 | 6000 min. |
| Elongation (%) | ASTM-D638 | 100 min. |
| Heat Distortion Temp. (°F@264psi) | ASTM-D648 | 152 ± 5 |
| Vicat Softening Temp. (°C) | ASTM-D1525 | 89 ± 2 |

The application suggestions, specifications and other data described here are based on experience that is believed by Tekra Corporation and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.