





I90159

PRODUCT DATA

YUPOBlue® 5.9pt 78LB Text

YUPOBlue is made specifically and certified at RIT to run on the HP Indigo line of digital printers. YUPOBlue is superior among synthetics for dimensional stability. It is bright white, super smooth and durable. It is stain resistant, 100 percent waterproof and resists stretching

| Parameter | | Units | Range | Reference |
|-----------------------|-------|----------|---------------|-------------|
| Thickness, Average | | micron | 150 +/- 8 | JIS P-8118 |
| Basis Weight, Average | | g/m2 | 115.5 +/- 6.0 | JIS P-8124 |
| Opacity, Average | | % | 94.5 min. | TAPPI T-425 |
| Gloss Average | - Top | % | 23 +/- 4 | TAPPI T-480 |
| | -Back | % | 23 +/- 4 | TAPPI T-480 |
| Whiteness, Average | | WI | 93.0 min. | JIS L-1015 |
| Tensile Strength | -MD | kgf/15mm | 9.0 min. | TAPPI T-494 |
| | -TD | kgf/15mm | 23.5 min. | TAPPI T-494 |
| 5% Elongation | -MD | kgf/15mm | 4.4 +/- 1.4 | TAPPI T-494 |
| | -TD | kgf/15mm | 11.7 +/- 4.0 | TAPPI T-494 |
| Tear Strength | -MD | gf | 63.0 +/- 17.0 | TAPPI T-414 |
| | -TD | gf | 31.5 +/- 9.5 | TAPPI T-414 |
| Clark Stiffness | -MD | s-value | 48.0 min. | TAPPI T-451 |
| | -TD | s-value | 97.0 min | TAPPI T-451 |

The application suggestions, specifications and other data described here are based on experience that is believed by Tekra Corporation to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.