



Wide Format UV Inkjet Media

Product Data

JetView™ Clear Polyester for UV Inkjet

Product Description

JetView Clear Polyester is for UV Inkjet printers. The film is a dimensionally stable, image enhancing clear film that can be printed on the front, back, or both sides.

Typical Applications

Reverse printed light boxes, window displays, illuminated signs, point-of-purchase signs.

Available Gauges (stocked & custom):

500, 700, and 1000 gauge

Polyester Data:

Property	Value	Units	Test
Optical			
Haze	0.4	%	ASTM D1003
TLT	88	%	ASTM D1003
Physical			
C.O.F. (dynamic) A-B	0.5		ASTM D1894
Elongation at Break MD	200	%	ASTM D882A
Elongation at Break TD	120	%	ASTM D882A
Tensile Strength MD	24,000	psi	ASTM D882A
Tensile Strength TD	30,000	psi	ASTM D882A
Yield Strength MD	14,000	psi	ASTM D882A
Yield Strength TD	14,000	psi	ASTM D882A
Thermal			
Shrinkage MD (190°C)	1.7	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)	1.9	%	Unrestrained @ 190°C/5 min

In the event of any post-print processing applications, a minimum of 24 hours is recommended between printing and any additional processes. This is especially important for any processes that will come in direct contact with the ink, such as adhesive lamination. For best results, consult your ink manufacturer's recommendation of ink post-cure time, as inks may vary.

The applications suggestions, specifications and other data described here are based on experience that is believed by Tekra and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Seller's terms and conditions of sale.