



## Wide Format UV Inkjet Media

## Product Data

### JetView™ White Polyester for UV Inkjet

#### Product Description

JetView White Polyester is for UV Inkjet printers. The film has superb handling properties and is pre-treated on both both sides for optimal ink adhesion

#### Typical Applications

Point-of-purchase signs, banners, posters, roll up displays

#### Available Gauges (stocked & custom):

500, 700, and 1000 gauge

#### Polyester Data:

Property	Thickness	Value	Units	Test
<b>Optical</b>				
Gloss 45 Degrees	700	40	%	ASTM D1003
Gloss 60 Degrees	700	45	%	ASTM D1003
TLT	700	6	%	ASTM D1003
Whiteness	700	100		ASTM E313-79
<b>Physical</b>				
Density	700	1.48	g/cc	ASTM D1505
Elongation at Break MD	700	135	%	ASTM D882A
Elongation at Break TD	700	90	%	ASTM D882A
Tensile Strength MD	700	22,000	psi	ASTM D882A
Tensile Strength TD	700	23,000	psi	ASTM D882A
Yield (nominal)	700	2,800	ln <sup>2</sup> /lb	
<b>Thermal</b>				
Shrinkage MD	700	1.5	%	Unrestrained @ 190°C/5 min
Shrinkage TD	700	1.5	%	Unrestrained @ 190°C/5 min

In the event of any post-print processing applications, a minimum of 24 hours is recommended between printing and any additional processes. This is especially important for any processes that will come in direct contact with the ink, such as adhesive lamination. For best results, consult your ink manufacturer's recommendation of ink post-cure time, as inks may vary.

The applications suggestions, specifications and other data described here are based on experience that is believed by Tekra Corporation and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Seller's terms and conditions of sale.