



Hanita Coatings



Wide Format Solvent Based Inkjet Media

M10076B

Product Data

5mil Semi-Matte Opaque Polyester for Duplex Printing

Applications: - Double sided banners
- Exhibit Flags
- Flexible Barriers

Benefits: - 100% opacity for perfect printing on both sides
- Robust handling properties
- Excellent print resolution and anchorage
- No overlaminates required

Printable By: - Solvent and UV wide format printers such as but not limited to:

- Mimaki JV3
- Roland Soljet
- Gandiinnovations
- HP Scitex TJ UV
- Efi Vutek
- HP Scitex TJ/PJ
- HP 8000
- Durst Rho 160

Product Specifications:

Item #	Base Film Thickness	Area Yield	Total Light Transmission	Appearance	Tensile Strength		Elongation at Break		Shrinkage	
					MD*	TD*	MD*	TD*	MD*	TD*
M10076B	5.3	4.2	<0.1	Semi matte white	24,200	25,600	120	100	1.5	0
Units	mil	msi/lb	%	.	psi		%		%	
Test Method	--	--	ASTM D 1003	--	ASTM D882-83		ASTM D882-83		After 5 minutes at 190C	

In the event of any post-print processing applications, a minimum of 24 hours is recommended between printing and any additional processes. This is especially important for any processes that will come in direct contact with the ink, such as adhesive lamination. For best results, consult your ink manufacturer's recommendation of ink post-cure time, as inks may vary.

The applications suggestions, specifications and other data described here are based on experience that is believed by Tekra and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions. Any order for these products will be subject to Seller's terms and conditions of sale.