

# DURAVIEW

Wide Format Solvent Based Inkjet Media

V3G005

## Product Data

### 5mil White Glossy Yupo®

Applications: - Wide format posters  
- Backlit media for scrollers or light boxes

Benefits: - Excellent print resolution and anchorage  
- Lighter weight and more durable than other media  
- For use with pigment ink for high resistance to weathering

Printable By: - Solvent and Ecosolvent wide format printers such as but not limited to:

- Mimaki JV3 SP
- Roland Soljet
- Seiko 64S
- Scitex Vision Grandjet
- Scitex Vision Pressjet
- Scitex Vision Idanit
- Plus other ecosolvent printers

#### Product Specifications:

Item Number	Apperance	Base Film Thicknes	Area Yield	Tensile Strength		Elongation at Break		Heat Resistance
				MD	TD	MD	TD	
V3G005	White Matte	5 mil	10	11	30	120	25	Polyolefinic based film should not be used at temperatures over 80° C
Units		µm	m <sup>2</sup> /Kg	Kg/mm <sup>2</sup>		%		
Test Methods				ASTM D 882-83		ASTM D 882-83		

In the event of any post-print processing applications, a minimum of 24 hours is recommended between printing and any additional processes. This is especially important for any processes that will come in direct contact with the ink, such as adhesive lamination. For best results, consult your ink manufacturer's recommendation of ink post-cure time, as inks may vary.

The applications suggestions, specifications and other data described here are based on experience that is believed by Tekra and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Seller's terms and conditions of sale.