



Hanita Coatings



Wide Format Solvent Based Inkjet Media

V8C202

Product Data

2mil Clear Polyester with Removable Adhesive

- Applications:
- Window Graphics
 - Decorative Applications
 - Exhibition Graphics
 - Promotional graphics
 - Interior Design

- Benefits:
- Excellent print resolution and anchorage
 - High Clarity and Gloss
 - Robust handling properties
 - Waterproof
 - Stable, heat resistant polyester film ensures no creeping or wrinkles

- Printable By: - Solvent and Ecosolvent wide format printers such as but not limited to:
- Mimaki JV3
 - Roland Soljet
 - Seiko 64S
 - Arizona
 - Scitex Vision Pressjet and Novo
 - Durst Rho 160

Product Specifications:

Item Number	Apperance	Base Film Thicknes	Area Yield	Tensile Strength		Elongation at Break		Heat Resistance	
				MD	TD	MD	TD	MD	TD
V8C202	Clear	2 mil	8.2	20	23	125	80	2	1
Units		µm	m ² /Kg	Kg/mm ²		%		%	
Test Methods				ASTM D 882-83		ASTM D 882-83		30 min at 130° C	

In the event of any post-print processing applications, a minimum of 24 hours is recommended between printing and any additional processes. This is especially important for any processes that will come in direct contact with the ink, such as adhesive lamination. For best results, consult your ink manufacturer's recommendation of ink post-cure time, as inks may vary.

The applications suggestions, specifications and other data described here are based on experience that is believed by Tekra and Hanita Coatings to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Seller's terms and conditions of sale.