

Marnot films are a complete line of functional hardcoats designed for graphic arts applications.

Features of Marnot XL Matte Polycarbonate include:

- Available in 20, 35, 55, 75 and 90 GU matte levels
- Excellent abrasion and scratch resistance
- Outstanding for embossing and die cutting
- Excellent chemical resistance to common household cleaners and industrial solvents
- Second surface printability with solvent and UV inks
- First surface printability with clear, matte and texture UV cure inks

Marnot XL Matte Polycarbonate is available in web width of 48" and in 7, 10, 15, 20 and 30 mil thickness.

Custom roll widths and sheet sizes available.

TYPICAL VALUES [‡]				
Physical	Test Method	Value	Unit	
Specific Gravity	ASTM D792	1.2	g/cm3	
Area Factor (Yield Factor)		0.0433	Ĺb/in3	
Clarity	TM 10.76	65-60-50-40-	%	
Haze	TM 10.76	35 10-13-20-37- 50	%	
Light Transmission	TM 10.76	91	%	
Gloss Back painted Flat Black 60 Degrees	TM 10.15	55-45-33-20- 10	GU	
Gloss Clear Over White Matte 60 degrees	TM 10.15	90-75-55-35- 20	GU	
Mechanical	Test Method	Value	Unit	
Abrasion Resistance	TM 10.13	< \Delta 9		
Pencil Hardness	TM 10.97	HB		
Tensile Strength at Yield	ASTM D882	8400	psi	
Break		8800	psi	
Tear Strength at Initiation	ASTM D1004	640	g/mil	
Tear Strength at Propagation	ASTM D1922	30	g/mil	
Thermal	Test Method	Value	Unit	
Glass Transition		153	С	
Shrinkage MD TD	30 min at 120C	0.1 0.1	% %	

[‡] These are typical values only and should not be confused with specification values. Specifications, tolerances

And minimum values are available on request from your Tekra representative or from Tekra.

POST UV CURING CHEMICAL RESISTANCE

Observiced	0	4 1	
Chemical	One Hour	4 hours	
	Surface	surface	
	Contact at	contact at	
	23C	23C	
Acetone	Pass	Pass	
Concentrated HCI	Pass	Fail	
MEK	Pass	Pass	
Toluene	Pass	Pass	
Methylene Chloride	Pass	Pass	
Isopropyl Alcohol	Pass	Pass	
Cyclehexanone	Pass	Pass	
Ethyl Acetate	Pass	Pass	
Xylene	Pass	Pass	
Brake Fluid	Pass	Pass	
Butyl Cellosolve	Pass	Pass	
Hexane	Pass	Pass	
	24 Hours	24 hours	
	Surface	surface	
	Contact at	contact at	
	23C	50C	
Coffee	Pass	Slight Stain	
Fantastik ¹	Pass	Pass	
Formula 409 ²	Pass	Pass	
Windex w/ Ammonia D ¹	Pass	Pass	
Tide ³	Pass	Pass	
Downy ³	Pass	Pass	
20% Bleach	Pass	Pass	
Mustard	Pass	Stain	
Mr. Clean ³	Pass	Pass	
Ketchup	Pass	Pass	
Теа	Pass	Slight Stain	
Tomato Juice	Pass	Pass	
Lemon Juice	Pass	Pass	
Grape Juice	Pass	Slight Stain	
Vinegar	Pass	Pass	
Milk	Pass	Pass	
Armor All [†]	Pass	Pass	
Ethanol	Pass	Pass	
Salt Water	Pass	Pass	
Sunscreen	Pass	Pass	

¹ Registered Trademark of SC Johnson

- ² Registered Trademark of the Clorox Company
- ³ Registered Trademark of Proctor and Gamble
- [†] Registered Trademark of ArmorAll Products Corp.

MASKING AND INTERLEAVING

Marnot XL Matte PC can be configured with mask on the second surface, or with mask on the first and second surfaces. If no protective masking is selected, Tekra will not warranty against spot abrasions or other damage to the uncoated surface in transit.

PROCESSABILITY

Tekra has made a good faith effort to validate the suitability of this product with common processing methods including screen printing, laser cutting, die cutting and embossing. However, because of the variability between different types of equipment, methods and processing conditions Tekra recommends that you work with your Tekra representative, your ink representative and your machine manufacturer to determine the substrates, inks, machinery and settings that work best in your particular situation.

The application suggestions, specifications and other data described here are based on experience that is believed by Tekra Corporation to be reliable. Because of the characteristics of these products, you should, before using these products in production, perform your own tests to determine to your satisfaction whether these products are acceptable and suitable for your particular purposes under your operation conditions.

Any order for these products will be subject to Tekra's terms and conditions of sale.

Version 1.5 - October 2016



Tekra LLC 16700 W Lincoln Ave New Berlin, WI 53151 800-448-3572