

[Show Printable Version](#)

## MYLAR® EL21

### Product Description

Mylar® EL21 polyester films are flexible strong and durable films with an unusual balance of properties, making them suitable for a variety of industrial applications. The excellent dielectric strength, moisture resistance, and physical toughness make Mylar® EL21 a very versatile and functional insulating material.

### General Product Info

Mylar® EL21 films offer high dielectric strength, good chemical resistance, and exceptional durability in high-temperature environments.

### Typical Applications

Mylar® type EL21 films, similar to Mylar® type MO films, are heavy gauge insulating films designed for general purpose electrical/electronic applications, such as transformers, laminates, bus bars, and punched parts.

### Approvals

**UL Recognition** - Product has been registered with Underwriters Laboratories.

### Typical Properties

Available Thickness [Gauge]
750; 900; 1000; 1400

Property	Thickness	Value	Units	Test
<b>ELECTRICAL</b>				
Breakdown Voltage	750	17.5	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Breakdown Voltage	900	18.4	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Breakdown Voltage	1000	19.0	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
Breakdown Voltage	1400	20.0	kV	ASTM D149 1/4" electrode 500 V/sec 25°C in air
<b>OPTICAL</b>				
Opacity	750	38	%	optical density
Opacity	900	41	%	optical density
Opacity	1000	42	%	optical density
Opacity	1400	46	%	optical density
<b>PHYSICAL</b>				
Density	750	1.3928	g/cc	
Density	900	1.3920	g/cc	
Density	1000	1.3925	g/cm3	
Density	1400	1.3925	g/cc	
Elongation at Break MD	750	140	%	ASTM D882A
Elongation at Break MD	900	150	%	ASTM D882A
Elongation at Break MD	1000	150	%	ASTM D882A
Elongation at Break MD	1400	170	%	ASTM D882A
Elongation at Break TD	750	115	%	ASTM D882A
Elongation at Break TD	900	130	%	ASTM D882A
Elongation at Break TD	1000	140	%	ASTM D882A
Elongation at Break TD	1400	170	%	ASTM D882A
Tensile Strength MD	750	27	kpsi	ASTM D882A
Tensile Strength MD	900	27	kpsi	ASTM D882A
Tensile Strength MD	1000	27	kpsi	ASTM D882A

Tensile Strength MD	1400	26	kpsi	ASTM D882A
Tensile Strength TD	750	30	kpsi	ASTM D882A
Tensile Strength TD	900	29	kpsi	ASTM D882A
Tensile Strength TD	1000	29	kpsi	ASTM D882A
Tensile Strength TD	1400	25	kpsi	ASTM D882A
Yield (nominal)	750	2,600	in <sup>2</sup> /lb	
Yield (nominal)	900	2,200	in <sup>2</sup> /lb	
Yield (nominal)	1000	2,000	in <sup>2</sup> /lb	
Yield (nominal)	1400	1,400	in <sup>2</sup> /lb	
<b>THERMAL</b>				
Shrinkage MD (150°C)	750	1.6	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	900	1.6	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	1000	1.5	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	1400	1.3	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	750	0.9	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	900	1.1	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	1000	1.1	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	1400	0.8	%	Unrestrained @ 150°C/30 min

#### Standard Put-ups

Core I.D. (Inches)	Roll O.D. (Inches)	Thickness (Gauge)	Length (Feet)
3	13	750	1,360
3	13	900	1,140
3	13	1000	1,020
3	13	1400	730
10 (Master roll)		750	5,400
10 (Master roll)		900	4,520
10 (Master roll)		1000	4,070
10 (Master roll)		1400	2,850

#### Contact Info

DuPont Teijin Films U.S. Limited Partnership  
3600 Discovery Drive  
Chester, VA 23836 USA  
Tel: (800) 635-4639  
Fax: (804) 530-9867

#### Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership.

 [Show Printable Version](#)

Copyright © 2006 DuPont Teijin Films. All rights reserved. | [Privacy](#)  
Developed and Powered by Client Centered Technologies, Inc.