



MYLAR® RSXR951

Product Description

MYLAR® RSXR951 is a silicone coated polyester film containing recycled silicone-coated liner designed for use as a release liner in various casting applications. The silicone release coating is applied to the film during the film production process, providing excellent adhesion of the coating to the polyester film for improved liner performance.

General Product Info

MYLAR® RSXR951 has balanced tensile properties and good dimensional stability. Release values typically range between 5 and 25 grams per inch when tested with aggressive pressure-sensitive adhesives. It is recommended that the liner be tested in each application to verify the absolute value of the release strength.

Typical Properties

Available Thickness [Gauge]
75; 92; 105; 120; 140; 142; 200; 300

Property	Thickness	Value	Units	Test
OPTICAL				
Haze	75 - 92	5.6	%	ASTM D1003
Haze	120	6.9	%	ASTM D1003
Haze	140-142	7.5	%	ASTM D1003
Haze	200	9.0	%	ASTM D1003
Haze	300	12.0	%	ASTM D1003
PHYSICAL				
Elongation at Break MD	75 - 120	140	%	ASTM D882A
Elongation at Break MD	140 - 300	150	%	ASTM D882A
Elongation at Break TD	75 - 120	100	%	ASTM D882A
Elongation at Break TD	140 - 300	110	%	ASTM D882A
Peel Strength	ALL	6-15	g/25 mm	Using Tesa 7475 Tape
Tensile Strength MD	ALL	28.0	kpsi	ASTM D882A
Tensile Strength TD	ALL	34.0	kpsi	ASTM D882A
THERMAL				
Shrinkage MD (150°C)	75 - 142	2.1	%	Unrestrained @ 150°C/30 min
Shrinkage MD (150°C)	200 - 300	1.8	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	75 - 142	0.5	%	Unrestrained @ 150°C/30 min
Shrinkage TD (150°C)	200 - 300	0.7	%	Unrestrained @ 150°C/30 min

Contact Info

DuPont Teijin Films U.S. Limited Partnership
 3600 Discovery Drive
 Chester, VA 23836 USA
 Tel: (800) 635-4639
 Fax: (804) 530-9867

Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture

products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership.