# **DPF 50WD Clear Vinyl Film**

#### **Promotional Removable Film**

DPF 50WD is a 4-mil (100 micron) clear vinyl film with a clear low tack removable pressure-sensitive adhesive. The low tack adhesive is designed to bond well to glass surfaces while removing cleanly in a wide range or temperatures. DPF 50WD has a premium moisture stable polycoated lay-flat liner that is optimal for printing on a variety of print systems. DPF 50WD is rated for outdoor durability up to 2 years (unprinted). Printed durability is dependent on the ink system used.

## **APPLICATIONS & FEATURES**

- Window advertising and decals.
- Displays on high energy substrates such as glass, aluminum or other metals.
- Horizontal POP applications (excluding floor graphics).
- Digital printing with a wide variety of direct print systems, such as solvent, UV, and UV screen.
- Compatible with Series 3200.

### **PERFORMANCE & PHYSICAL DATA**

| PROPERTY                         | TEST METHODS  | TYPICAL VALUE      |              |
|----------------------------------|---|--------------------|--------------|
| SURFACE FINISH                   | Gloss Meter 60° Reflection  | 99%                |              |
| THICKNESS                        | Micrometer, Federal Bench Type  | 4-mil (100 micron) |              |
| TENSILE STRENGTH                 | Tensile Tester 2-in (51mm) jaw seperation; crosshead speed of 12 in/min. (5.1 mm/s) | 22.0 lb/in         | 3.93 kg/cm   |
| ELONGATION                       | Instron Tensile Tester as above   | 250%               |              |
| SHELF LIFE                       | Free from excessive moisture, temperature, direct sunlight                          | 2 Years            |              |
| APPLICATION TEMPERATURE<br>RANGE | On clean, dry substrate   | 50°F – 90°F        | 10°C – 30°C  |
| SERVICE<br>TEMPERATURE RANGE     | On clean, dry substrate   | -20°F – 176°F      | -29°C – 80°C |
| DIMENSIONAL STABILITY            | Shrinkage After 158°F (70°C), 48 hours aging  | 25 mils            | 0.635 mm     |
| PEEL ADHESION                    | PSTC-1, 15 min, RT 70°F (21°C)  | 0.16 lb/in         | 0.03 kg/cm   |
| LINER RELEASE                    | TLMI Release at 90°, 300 in/min (760 cm/min)  | 25 g/2 in          | 4.92 g/cm    |

\*Standard Terms & Conditions Apply

Effective Date 10/11

## TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

#### www.arlon.com