

DPF 2400 Reflective Vinyl Film

Reflective Digital Print Pressure Sensitive Film

DPF 2400 is a 5-mil (125 micron) printable reflective vinyl film with high initial tack and permanent pressure-sensitive adhesive. The film conforms well to both flat and irregular surfaces when processed and applied according to Arlon recommendations. DPF 2400 is rated for outdoor durability up to 7 years (unprinted) for flat surfaces and up to 5 years (unprinted) for irregular surfaces. Printed durability is dependent on the ink system used.

APPLICATIONS & FEATURES

- Digital printing with a wide variety of direct print systems
- Motor and railway coaches, fleet and vehicle markings, and any surface requiring reflective vinyl film

PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
SURFACE FINISH	Gloss Meter 60° Reflection	80 - 90%	
THICKNESS	Micrometer, Federal Bench Type	5-mil (125 micron)	
TENSILE STRENGTH	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥10.0 lb/in width	≥1.8 kg/cm width
ELONGATION	Instron Tensile Tester as above	≥110%	
SHELF LIFE	Free from excessive moisture, temperature, direct sunlight	2 years from factory shipment	
APPLICATION TEMPERATURE RANGE	On clean, dry substrate	60°F to 90°F optimum	16°C to 32°C optimum
SERVICE TEMPERATURE RANGE	On clean, dry substrate	-65°F to 160°F	-54°C to 71°C
HUMIDITY RESISTANCE	1. LS-300 Method 4.4.10 2. ASTM-D4956-89	No appreciable effect	
FUNGUS RESISTANCE	1. LS-300 Method 4.4.12 2. ASTM-D4956-89	No appreciable effect	
GASOLINE RESISTANCE	Film applied to etched aluminum panels 24 hours prior to testing LS-300 Method 4.4.6	No appreciable effect	
PEEL ADHESION	PSTC-1, 15 min. RT 70°F (21° C)	≥4.4 lbs/in	≥0.78 kg/cm
LINER RELEASE	TLMI Release at 90°, 300 in/min (60 cm/min)	40 g/2 in	8 g/cm

*Standard Terms & Conditions Apply

Effective Date 10/11

USA: 2811 S. Harbor Blvd. Santa Ana, CA 92704 – Telephone: 800-854-0361 – Fax: 714-540-7190

Customer Service: Telephone: 800-232-7161 – Fax: 800-329-2756 – Technical Services: 877-275-6698

EUROPE: Badhuisweg 11 2587 CA Den Haag, The Netherlands – Telephone: +31 (0) 70 354-4311 – Fax: +31 (0) 70 355-7721

INDIA: 4F1 Court Chambers, 35 - New Marines Lines, Mumbai 400 020 – Telephone: +91 99 6755-3895

www.arlon.com

TERMS & CONDITIONS

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

USA: 2811 S. Harbor Blvd. Santa Ana, CA 92704 – Telephone: 800-854-0361 – Fax: 714-540-7190

Customer Service: Telephone: 800-232-7161 – Fax: 800-329-2756 – Technical Services: 877-275-6698

EUROPE: Badhuisweg 11 2587 CA Den Haag, The Netherlands – Telephone: +31 (0) 70 354-4311 – Fax: +31 (0) 70 355-7721

INDIA: 4F1 Court Chambers, 35 - New Marines Lines, Mumbai 400 020 – Telephone: +91 99 6755-3895

www.arlon.com